

HPM - Selected Drill Intercepts

	from	to	Length*	Nickel	Copper	Cobalt
Drill Hole	(m)	(m)	(m)	(%)	(%)	(ppm)
HPM 08-01	78.6	84.07	5.47	2.34	0.97	1237
HPM-08-03	79.82	123	43.18	1.74	0.9	904
HPM-08-04	47.73	62.79	15.06	1.72	0.66	888
HPM-08-04	125.4	130.5	5.1	1.23	0.47	636
HPM-08-04	136.75	139.4	2.65	2.08	1.24	1072
HPM-08-04	144.17	148.22	4.05	2.31	1.35	1131
HPM-08-09	37.97	40.85	2.88	0.24	0.1	156
HPM-08-09	147.75	149.4	1.65	2.39	0.88	1250
HPM-08-11	47.27	48.78	1.51	2.2	0.77	1133
HPM-08-11	101.46	104.61	3.15	1.91	0.37	842
HPM-08-11	109.93	111	1.07	2.2	0.44	1083
HPM-08-11	140.2	141.5	1.3	0.72	0.1	448
HPM-08-11	142.5	144.2	1.7	0.33	0.16	211
HPM-08-17	132.25	134.2	1.95	2.69	2.61	1170

Source: Manicouagan Minerals Inc. HPM/Forges Project Preliminary Report, December 31, 2008. * Not Ture Width